



♣ Aone PP Dan Rope ♣      ◆Korea-PDF File ◆ ◆English-PDF File ◆

<b>Structure</b>	<b>Applications</b>
	Mooring, Towing, Tug lines, Anchor lines
	<b>Feature</b>
	<p>① Radiation is the latest fishing equipment Denny uniform product consistency, and high strength.</p> <p>② In Use of water does not absorb light, handling is excellent.</p> <p>③ Products produced in the process of fitting the job fair is excellent durability and wear resistance.</p>
 <p style="text-align: center;">8연                  12연</p>	

Physical Properties				
Fiber	Construction	Melting Point	Elongation at break	Specific gravity
Polypropylene danline fiber	8 strand, 12 strand	165 °C	30%	0.91 Floating

**Aone PP Dan 8 Strand Rope**

item No.	Dia.		Breaking Strength		Cir.		Weight	
	mm	Inch	KG	LBS	mm	Inch	kg/100m	lbs/100ft
ADR840	40	1-9/16	22,300	49,000	120	5	71.5	48.0
ADR844	44	1-3/4	26,900	59,000	132	5-1/2	88.5	59.5
ATR848	48	1-7/8	31,300	69,000	144	6	104.0	70.0
ADR852	52	2-1/16	36,200	79,800	156	6-1/2	122.0	82.0
ADR856	56	2-1/4	42,300	93,000	168	7	142.0	95.4
ADR860	60	2-3/8	48,500	107,000	180	7-1/2	163.0	109.5
ADR864	64	2-1/2	52,300	113,000	192	8	185.0	124.3
ADR872	68	2-3/4	68,000	150,000	216	9	230.0	154.6
ADR872	72	2-7/8	84,000	185,000	240	10	290.0	195.0
ADR888	88	3-7/16	97,500	215,000	264	11	351.0	236.0
ADR896	96	3-13/16	119,400	263,000	288	12	417.0	280.0
ADR810	104	4-1/8	140,200	309,000	312	12-3/4	490.0	329.3
ADR811	112	4-7/16	162,600	358,000	336	14	568.0	381.7

**Aone PP Dan 12 Strand Rope**

item No.	Dia.		Breaking Strength		Cir.		Weight	
	mm	Inch	KG	LBS	mm	Inch	kg/100m	lbs/100ft
ADR040	40	1-9/16	22,000	48,500	120	5	75.5	50.7
ADR044	44	1-3/4	26,000	57,000	132	5-1/2	92.0	62.0
ADR048	48	1-7/8	28,000	62,000	144	6	108.0	72.6
ADR052	52	2-1/16	35,000	77,000	156	6-1/2	128.0	86.0
ADR056	56	2-1/4	41,000	90,000	168	7	148.0	99.5
ADR060	60	2-3/8	47,000	103,000	180	7-1/2	170.0	114.2
ADR064	64	2-1/2	53,000	117,000	192	8	195.0	131.0
ADR072	72	2-7/8	67,000	148,000	216	9	245.0	164.6
ADR080	80	3-5/32	82,000	181,000	240	10	303.0	203.6
ADR088	88	3-7/16	96,000	211,500	264	11	366.0	246.0
ADR096	96	3-13/16	116,000	255,500	288	12	436.0	293.0
ADR010	104	4-1/8	128,000	282,000	312	12-3/4	511.0	343.0
ADR011	112	4-7/16	146,000	322,000	336	14	612.0	411.0